

## Technical Data Sheet

<b>Name</b>	<b>DeoAdd C 111</b>	
<b>Description</b>	non emulsifying, water displacing Rust Preventive	
<b>Active Substance</b>	mixture of oxidized esters and sulfonates	
<b>Appearance</b>	brown greasy solid substance	
<b>Analytical Value</b>		
Solidification point (°C)	DIN ISO 2207	27 - 38
Acid No. (mg KOH/g)	DIN 51558 part1	2 - 8
Saponification No. (mg KOH/g)	DIN EN ISO 3681	55 - 75
Density at 20°C (g/cm <sup>3</sup> )	DIN ISO 787 part 10A	0.9
Flashpoint (°C)	DIN ISO 2592	min. 140
<b>Treat Rate</b>	5 - 20 % in mineral spirit or mineral oil	
<b>Supply Form</b>	190 kg in steel drums	
<b>Shelf Life</b>		
In originally sealed packages at room temperature	max. 2 years	
<b>Behaviour and effects</b>	<ul style="list-style-type: none"> <li>- Non emulsifying, water displacing Rust Prevention.</li> <li>- Excellent rust and corrosion protection.</li> </ul>	
<b>Application</b>	<ul style="list-style-type: none"> <li>- For metal parts after emulsion treatment to displace water residues from the metal surface. Rust Preventive for intermediate storage.</li> <li>- Ferrous and non-ferrous metal protection.</li> </ul>	

Any technical consultation provided by us merely constitutes a guideline without any committal - even with regard to any third party's rights - and will not dispense from the client's examination of the products supplied by us. Processing operations, application and use of our products will be the client's exclusive responsibility. We guarantee the faultless quality of our goods, as defined in our General Terms of Sale and Delivery.

Valid March 4<sup>th</sup>, 2005