

## Technical Data Sheet

<b>Name</b>	<b>Deosicc® Zn 12 N</b>	
<b>Description</b>	Corrosion inhibitor	
<b>Active Substance</b>	Zincnaphthenate in mineral oil	
<b>Appearance</b>	light brown viscous liquid	
<b>Analytical values</b>		
Zinc (%)	DIN 55901 chapter 8.4	11.9 – 12.1
Kinematic Viscosity at 100 °C (mm <sup>2</sup> /s)	DIN EN ISO 3104	10 - 50
Density at 20°C (g/cm <sup>3</sup> )	DIN ISO 787, part 10 a	1.00 – 1.05
Corrosion prevention in artificial seawater	DIN 51585	0
<b>Dosage</b> (phr)	0.5 – 3 %	
<b>Supply Form</b>	200 kg in bung hole steel-drums	
<b>Storage Stability</b>		
In originally sealed package at room-temperature	min. 6 months	
<b>Application</b>	Corrosion inhibitor for greases, as well as in hydraulic and gas engine oils.	

Any technical consultation provided by us merely constitutes a guideline without any committal - even with regard to any third party's rights - and will not dispense from the client's examination of the products supplied by us. Processing operations, application and use of our products will be the client's exclusive responsibility. We guarantee the faultless quality of our goods, as defined in our General Terms of Sale and Delivery.

Valid 2003-02-28