

Data sheet

**GRADE
B 600**

ARBOCEL[®]

natural cellulose fibres

Basic raw material

highly pure cellulose

Characteristic

short fibre, white

Physical and chemical properties

cellulose content	approx. 99,5 %
average fibre length	60 µm
average fibre thickness	20 µm
bulk density	180 g/l - 220 g/l
whiteness (absolute value at 461 nm)	86 % +/- 5 %
residue on ignition (850 °C, 4 h)	approx. 0,3 %
pH-value	6 +/- 1

Screen analysis

Screen residue (in accordance with DIN 53 734/air jet sieve) with an interior mesh aperture of:

<u>200 µm</u>	<u>100 µm</u>	<u>32 µm</u>
max. 0,5 %	max. 3 %	max. 30 %

As with all natural products slight differences to the above given values may arise.

General references

ARBOCEL[®] cellulose fibres are environment friendly products, gained from replenishable raw materials.

Among other things, they are used as thickeners, for fibre reinforcement, as an absorbent and diluent or as a carrier and filler in most manifold application fields.

CAS-Nr.: 9004-34-6



J. RETTENMAIER & SÖHNE GMBH + CO
Manufacturers of Fibres
Holzmühle 1
D-73494 Rosenberg

Telephone: 0 79 67/1 52-0
Telefax: 0 79 67/ 1 52 - 222

9609