

# BRIDGE FIELDS RESOURCES SDN. BHD.

(Co. No. 809621-K)

OFFICE: 35-1, USJ 10/1G, TAIPAN CREST, 47620 SUBANG JAYA, SELANGOR, MALAYSIA

TEL: +60356338444 FAX: +603 56345333

E-Mail: [info@bridgefields.com](mailto:info@bridgefields.com) / [asmibudin@gmail.com](mailto:asmibudin@gmail.com)

## Producers of quality polymers

### 規格表

品名 : GRENVIRO – NRG 90P

成份 : 天然膠橡膠

製造商: BRIDGE FIELDS RESOURCES S/B

#### 膠料配方

物質	PHR
NRG 90P	100
ZnO	4
Stearic Acid	2.5
Sulphur	1
CBS	1
TMTD	0.1
Silica	10

#### 物性

拉伸強度 (Mpa)	12.8 ± 5
伸長率 (E.B)%	520 ± 100
比 重 %	1.08 ± 0.15
橡膠烴 %	85 ± 15
灰 份 %	15 ± 10
丙酮萃取 %	3 ± 1.5
門尼粘度	50 ± 15

# Grenviro

\*此規格表是產品在正常情況下提供

#### 包裝標準:

每包重量 : 25 Kgs

托盤包數 : 50 Bales

一托重量 : 1250 Kgs

每一包都裝在 LDPE 袋裡

#### 一櫃可裝數量:

FLC 20 尺櫃 (含棧板) : 20,000 Kgs

FLC 20 尺櫃 (不含棧板) : 25,000 Kgs

#### 保存:

保存在乾燥且密閉的空間，遠離加熱設備和存放至溫度低於 30°C 的環境。

防止產品陽光直射。在以上的儲存條件下，產品可以存放至 8 個月以上。



Included with its product literature and upon the request of its customers, BFR provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although BFR believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. BFR will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of BFR products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights or process. BFR CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY BFR.

Included with its product literature and upon the request of its customers, BFR provides product specifications and evaluations, suggested formulations and recommendations and other technical assistance, both orally and in writing (collectively the "Technical Information"). Although BFR believes all Technical Information to be true and correct, it makes no warranty, either express or implied, as to the accuracy, completeness, or fitness of the Technical Information for any intended use, or the results which may be obtained by any person using the Technical Information. BFR will not be liable for any cost, loss or damage, in tort, contract or otherwise, arising from customer's use of BFR products or Technical Information. It is the customer's sole responsibility to test the products and any Technical Information provided to determine whether they are suitable for the customer's needs. Before working with any product, the customer must read and become familiar with available information concerning its hazards, proper use, storage and handling, including all health, safety, and hygiene precautions recommended by the manufacturer. Nothing in the Technical Information is intended to be a recommendation to use any product, method, or process in violation of any intellectual property rights governing such product, method, or process. BFR CORPORATION DISCLAIMS ANY AND ALL WARRANTIES, EXPRESS AND IMPLIED, INCLUDING WITHOUT LIMITATION, WARRANTIES OF MERCHANTABILITY AND FITNESS FOR ANY PARTICULAR PURPOSE, RELATED TO ANY PRODUCTS OR TECHNICAL INFORMATION PROVIDED BY BFR.