

NR-80

List date:2019.10.31

Composition: Natural Rubber

Tensile Strength (Mpa): 15.8 ± 5

Elongation (E.B) %: 720 ± 60

Specific Gravity %: 1.02 ± 0.08

Rubber Hydrocarbon %: 80 ± 8

Ash%: 20 ± 5

Acetone Extract: %: 3 ± 1.5

Moony Viscosity: 48 ± 15

Package Standard:

Bag weight: 25 kgs

No. of bags per pallet: 50 bags

Carton weight: 1250 kgs

Package with a LDPE bag

Container

FLC 20'container (16 pallets) : 20,000 Kgs

FLC 20' container (without pallet) : 25,000 Kgs

Storage:

Store it in a dry and closed space at the temperature below 30°C , and keep it away from heating equipment. Avoid direct sunlight. With the above condition, it can be stored for more than eight months.