

Name	Homogenisator 501	
Description	tackifying resin	
Composition	polymerisates of unsaturated aromatic hydrocarbons	
Appearance	light yellow flakes	
Analytical Values		
Softening point (°C)	ASTM D 3461	100 ± 5
Density at 20°C (g/cm³)	DIN ISO 787 part 10 A	1.1
Ash (%)	DIN EN ISO 3451-1	max. 0.1
Dosage (phr)	3 – 15	
Solubility	soluble in aromatics, partly soluble in white spirit	
German Food Legislation (BgVV Recommendation XXI)	not approved	
Supply Form	25 kg in PE-bags	
Storage Stability		
In originally sealed package in cool and dry places	min. 1 year	
Behaviour and Effects		
Homogenisator 501 improves the homogeneity of rubber blends of polymers with different polarities and viscosities. It imparts to raw compounds better building tack and facilitates processing during mixing, extruding and calendering.		
Application		
As homogenizer for rubber blends and as tackifying resin for elastomers.		

Any technical consultation provided by us merely constitutes a guideline without any committal - even with regard to any third party's rights - and will not dispense from the client's examination of the products supplied by us. Processing operations, application and use of our products will be the client's exclusive responsibility. We guarantee the faultless quality of our goods, as defined in our General Terms of Sale and Delivery.

Valid February 11<sup>th</sup>, 2003