

# DIN-150A

List date:2019/10/30

**Composition:** Silane coupling agent and the polymer carrier

**Appearance :** white granules

**Specific Gravity:** Approx. 1.1

**Soften point:** >50°C

**MV.(ML1+4@100°C):**  $\leq 22$

**Storage Stability:** 1 Year under normal condition

**Package:** 20KG/ cardboard box

**Recommended Usage:** adding 3-8 phr into the formula; 6 phr under normal condition.

**Note:** It is effective in the peroxide crosslinking system, but the result is not significant in sulfur crosslinking system.

**Functions:**

Effectively improve the abrasion resistance of EVA foam rubber, and has a significant result on the NBS DIN abrasion resistance test.

**元慶國際貿易有限公司**

台中市崇德路二段 128 號 18 樓之 1

TEL:04-22381380 FAX:04-22381379

WWW.ANYKING.COM.TW

本指引僅供參考，因製程操作和使用將超過我們控制，故無法作任何承諾。