



RUBBOND 40

TECHNICAL DATA SHEET

Issue No
002/02

Revision Date
17.07.2018

產品名稱

RUBBOND 40

分類

深色芳香烴樹脂均質劑

物理性質

形狀 : 錠狀
外觀 : 黑色錠狀
比重@ 25C : 1.04 ± 0.04

化學性質

產品	RUBBOND 40
軟化點 (°C, R&B) 5°C/Minute	96 - 106
灰份 (% , Max) 750°C/2hrs	2 Max.

應用

RUBBOND 40均質劑提高了極性和粘度不同的彈性體的均勻性，在共混過程中，RUBBOND 40能被聚合物迅速吸收。對那些在混合開始時就容易變質的彈性體共混物特別有效。

在硫化過程中，RUBBOND 40不會增硬。硫化的硬度不會因使用礦物油增塑劑而降低太多。

RUBBOND 40降低了化合物的粘度和粘度，有助於下游加工。有時，在不增加擠出膨脹的情況下，可以降低袋狀傾向，提高擠出速率，改善壓延效能，即使在長時間貯存之綠色化合物(未硫化)後，這些優點仍會保留。

優勢

RUBBOND 40改善了模具流動和擠壓特性。減少收縮。改善彈性體和填料的均勻性。減少混合循環時間、能量耗損和粘度。提升綠色粘性。

儲存性

常溫密封貯存下，一年。

保值期

在正常儲存條件下，自製造之日起1年

包裝

25 kg (Net Wt) ， 袋裝/紙箱

健康與安全資訊

在操作之前請參閱安全資料表

Note:

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. RCPL gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that law prevents such exclusion.

RAJSHA CHEMICALS PRIVATE LIMITED

www.twc.in

Works:

Block No.: 637, Lamdapura Road, At. Manjusrar
PO: Lamdapura, Ta: Savli, Dist. Vadodara 391 775, India
Tel – +91 9662049271
Email – office@rajsha.com

Head Office:

3C Hi Tech Chambers, 84/1B Topsia Road (S)
Kolkata 700 046, West Bengal, India
Tel – 2285 1278 / 1279. Fax - +91 33 2285 1280
E mail – info@twc.in